## Magnetic Excitation of Possible Spin-Peierls System TiOBr

**T.** Yokoo<sup>a</sup>, S. Itoh<sup>a</sup>, F. Trouw<sup>b</sup>, A. Llobet-Megias<sup>b</sup>, J. Taylor<sup>c</sup>, and J. Akimitsu<sup>d</sup>

<sup>a</sup>IMSS, High Energy Accelerator Research Organization (KEK)

<sup>b</sup>Lujan Neutron Scattering Center, Los Alamos National Laboratory

<sup>c</sup>ISIS, Rutherford Appleton Laboratory

<sup>d</sup>Department of Physics, Aoyama-Gakuin University

Newly proposed spin-Peierls system TiOX (X: Cl, Br) has been revealed showing exotic structural and magnetic properties such as a successive phase transition, one-dimensional (1D) nature associated with orbital ordering of Ti ions and super-lattice structure being related to the Peierls instability. It is pointed out that resulting only from an arrangement of Ti  $d_{xy}$  orbital, the formation of 1D spin chains and the spin-Peierls transition will be realized. Recently, it has been demonstrated that TiOBr also exhibits two successive phase transitions similar to TiOCl at  $T_{c1}=27$  K and  $T_{c2}=47$  K. Here we carried out inelastic neutron experiments in order to see the evidence of spin-Peierls transition. The inelastic spectrum with a large amount of poly crystalline sample of TiOBr shows the localized signal in the vicinity of the magnetic zone center Q=0.9 Å<sup>-1</sup>. Observed spin gap like signal lies at energy of  $\Delta E \sim 10$  meV. The gap energy in TiOBr is expected much higher from measured thermodynamic properties and by analogy with TiOCl. Constant Q cuts of the observed S(Q, E) map show some Q-dependent structure in its intensity indicating the signal is sample oriented. The Q structure quite reveals the intensity is well explained by the powder averaged dynamical structure.